

Gels, Replay Gel and Crystal Gel

replaygel


Material Silicone gel
Expiry Date None
Re-enterable Yes
Mixing ratio 1:1
Voltage 0.6 kV · 1 kV
Temperature range -60 °C · 200 °C
Mixing time 12 mins (at 23 °C)
Curing time 20 mins (at 23 °C)
Colour Green
Protection from Rain, humidity, dust and animal intrusion



Replay Gel

Re-work gel

Gel, Replay Gel

Type	WISKA-No.	Description	
Replay Gel	MP0100R	2 part mix bottles	1 Ltr

crystalgel


Material Silicone gel
Expiry Date None
Re-enterable Yes
Mixing ratio 1:1
Voltage 0.6 kV · 1 kV
Temperature range -60 °C · 200 °C
Mixing time 12 mins (at 23 °C)
Curing time 20 mins (at 23 °C)
Colour Transparent
Protection from Rain, humidity, dust and animal intrusion



Crystal Gel

Transparent gel

Gel, Crystal Gel

Type	WISKA-No.	Description	
Crystal Gel	MP0100C	2 part mix bottles	1 Ltr