

Product Code: EG310**Description:** Solvent Based Bonding Adhesive Cartridge**Benefits**

Fast setting

- Has gap filling properties
- Adheres to virtually all common building surfaces
- Can be used internally or externally

A high strength, fast setting bonding adhesive with gap filling properties. Adheres to virtually all common building surfaces and can be used internally or externally. Replaces nails and screws in a multitude of applications, on rough or smooth surfaces.

Applications

Can be used to fix skirting boards, stair nosings, decorative wall paneling, door surrounds, timber cladding, floor boards, timber framework, worktops, floor grippers, door plates, brick cladding, veneer, mouldings, ceramics, plasterboard, cork, laminates and automotive trims.

Directions Of Use

Cut the cartridge seal and screw on the nozzle, which should be cut to your required size. Panel application - Apply the adhesive in 6mm beads, 5cm from the edge and approximately 20 - 40cm apart. Immediately press the panel firmly to the wall. Some support may be necessary for up to 24 hours. Stair nosings - Apply the adhesive in 6mm diameter beads to the nosings only. Small stair nosings will require two beads; larger stair nosings require three beads. Immediately press nosings into position and allow a drying period of 24 hours before subjecting to traffic.

Battens, skirting and other applications - Apply the adhesive equally in stripes, 20cm apart. Put the material in place, hold and move slightly, applying an even pressure, then press firmly into place. Some support may be necessary for up to 24 hours.

Limitations

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates

Cleaning

Uncured material, tools and hands can be cleaned with Multi-Purpose Cleaning Wipes. Cured material can only be mechanically removed.

Additional Information

Application temperature		+5°C to +25°C
Base		Styrenebutadiene rubber
Curing time	+ 23°C / 50% RH	72 hours
Density		1,40 g/ml
Frost resistance during transportation		Down to -15°C
Open time		3 - 5 minutes
Skin formation		3 - 5 minutes
Solids		83%
Temperature resistance		-30°C to +70°C
Usage		300 - 600 g/m ²

These values are typical properties and may vary +/-3%

Shelf Life

In unopened original packaging between + 5°C and + 25°C, shelf life is up to 12 months from production date, stored in a dry place.

Health & Safety

Safety data sheet (MSDS) must be read and understood before use of product. These are available on request.