

SFIRE - FIRE-RATED SILICONE SEALANT

Description:

Fire Rated Silicone which maintains the integrity of fire walls when breached by conduits, pipes, etc. High movement and halogen free.

Standard:

4 Hours tested to ISD 834 & to BS 476, Part 22

Additional Notes:

This product comes in only one size, which is stated below.



TECHNICAL DATA

Product Code	Type
SFIRE	310ml

Technical Data	
Base	Polysiloxane
Consistency	Stable Pasta
Curling System	Moisture Cure
Skin Forming	Ca 20 min (20°C/65% R.H.)
Curing Rate	1mm/24h
Shore a Hardness	16 Shore A
Specific Gravity	Ca 1. 17 g/cm ²
Temperature Resistance	-40°C until +140°C
Elongation at Break	900% (DIN52455)
E-Modulus 100%	0,20N/mm ² (DIN52455)
Elastical Recovery	>90% (DIN53455)
Maximum Deformation	+25

PRODUCT

Firesilicone B1 FR is a high quality, neutral, elastic, one component sealant based on silicones which conforms to the DIN4102 B1 Standard for fire retardancy and has a fire rating of up to 4 hours in certain joint configurations (EN 1366 Part 4 - NN713.020 - BS 476/20)

CHARACTERISTICS:

- Very easy to apply
- Colourfast and UV-resistant
- Remains Permanently elastic after full cure
- Very good adhesion on most surfaces
- Low modulus
- DIN 4102-Part 2: Class B1
- Up to 4 hours fire rating with normal PE backing material (see table enclosed)

Applications

All building and glazing joints which require a fire rating
Fire rate expansion joints

PACKAGING:

Colour: grey, white.

Packaging: cartridge 310ml, foil bag 600mL

SHELF LIFE:

9 Months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.
Do not expose to frost.

SURFACES

Type: all usual porous and non-porous building materials.

State of Surface: clean, dry, free of dust and grease

Preparation: porous substrates should be primed with Primer150. Soudal Surface Activator will improve adhesion on smooth surfaces.

We recommend a preliminary compatibility test.

JOINT SIZE:

Minimum Width: 5mm

Maximum Width: 30mm

Joint Configuration: Width = 2x depth

APPLICATION:

Method: caulking gun

Backing material: PE backer rods for correct joint dimension

Application temperature: +1°C to +30°C

Clean: with white spirit

Repair: with Firesilicone B1 FR

Finish: with soapy solution

HEALTH AND SAFETY

RECOMMENDATION:

Apply the usual industrial hygiene.

APPROVALS:

- Test report 9297 - University of Ghent
- NBN 713.020 - EN 1366-4
- BS 476:Part 20 - Warrington Fire Research Report
- DIN4102-B1 - Institut Fur Bautechnik, Berlin
- TINO-rapport 2000-CVB-R00703

Wall Thickness	Width of Joint	Depth of Joint	Application	Fire Rating
100mm	11mm	10mm	Doublesided	146 Min. TI Rating EI 120 202 min. FR Rating E 180
100mm	33mm	20mm	Doublesided	116 Min. TI Rating EI 90 187 min. FR Rating E 180
200mm	11mm	10mm	Doublesided	>240 Min. TI >240 min. FR Rating EI 240
200mm	31mm	20mm	Doublesided	>225 Min. Rating EL 180 >240 min. FR TI Rating E 240

TI = Thermal insulation; the time during which the temperature on the unexposed side of the wall does not rise by more than 180°C.

FR = FLame Resistance; the time during which the joints stops flames from penetrating the wall.

Fire Rating: Draft European Commission Decision RG N170 REV.1

Remark: The directives contained in this documentation are the result of our experiments and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Deligo Ltd 2017 - This document is provided to the public for information purposes only and is subjected to change without notice, Deligo Ltd make no promise of the document keeping the information contained within.

EMAIL: Sales@Deligo.co.uk

PHONE: +44 (0)1384 824 100

FAX: +44 (0)1384 825 077

FIXINGS, FASTENERS & ACCESSORIES FOR THE ELECTRICAL WHOLESALER

DELIGO

FIXINGS, FASTENERS & ACCESSORIES FOR THE ELECTRICAL WHOLESALER